

E-CF6

517-522

$n_d = 1.51742$ $\nu_d = 52.15$ $n_F - n_C = 0.009922$
 $n_e = 1.51978$ $\nu_e = 51.85$ $n_{F'} - n_{C'} = 0.010025$

屈折率 Refractive Index		
	λ (nm)	
n_t	1013.98	1.50650
n_s	852.11	1.50921
$n_{A'}$	768.19	1.51106
n_r	706.52	1.51275
n_c	656.27	1.51444
$n_{c'}$	643.85	1.51491
n_{633}	632.80	1.51535
n_D	589.29	1.51733
n_d	587.56	1.51742
n_e	546.07	1.51978
n_F	486.13	1.52436
$n_{F'}$	479.99	1.52493
n_g	435.84	1.52990
n_h	404.66	1.53461
n_i	365.01	1.54293

化学的性質 Chemical Properties	
D_W	2
D_A	1
T_{Blue}	1
D_{NaOH}	1
D_{STPP}	1
D_0	1
D_H	

内部透過率 Internal Transmittance		
λ (nm)	τ 5mm	τ 10mm
1550	0.996	0.993
1500	0.997	0.995
1400	0.997	0.995
1300	0.998	0.996
1200	0.999	0.998
1100	0.999	0.998
1060	0.999	0.998
1050	0.999	0.998
1000	0.999	0.998
950	0.999	0.998
900	0.999	0.998
850	0.999	0.998
830	0.999	0.998
800	0.999	0.998
780	0.999	0.998
750	0.999	0.998
700	0.998	0.996
650	0.997	0.994
600	0.998	0.996
550	0.998	0.996
500	0.995	0.990
480	0.995	0.989
460	0.993	0.986
440	0.993	0.986
420	0.993	0.985
400	0.991	0.982
390	0.989	0.978
380	0.983	0.967
370	0.969	0.939
360	0.920	0.847
350	0.748	0.559
340	0.387	0.150
330		
320		
310		
300		
290		
280		

分散式の定数 Constants of dispersion formula	
A_0	2.2668912
A_1	$-9.3866212 \times 10^{-3}$
A_2	1.2174195×10^{-2}
A_3	5.0769030×10^{-4}
A_4	$-3.3573414 \times 10^{-5}$
A_5	2.9059013×10^{-6}

熱的性質 Thermal Properties	
T_g (°C)	494
T_s (°C)	576
$T_{10^{14.5}}$ (°C)	471
$T_{10^{13}}$ (°C)	487
$T_{10^{7.6}}$ (°C)	681
$\alpha_{-30/+70}$ ($10^{-7}/K$)	82
$\alpha_{100/300}$ ($10^{-7}/K$)	92
λ [W/(m·K)]	0.970
C_p [kJ/(kg·K)]	0.715

部分分散 Partial dispersions	
$n_c - n_t$	0.007939
$n_d - n_c$	0.002984
$n_F - n_d$	0.006938
$n_g - n_F$	0.005545
$n_{c'} - n_t$	0.008412
$n_e - n_{c'}$	0.004871
$n_{F'} - n_e$	0.005154
$n_g - n_{F'}$	0.004969

機械的性質 Mechanical Properties	
H_K	495 (5)
F_A	150
E (GPa)	
G (GPa)	
μ	
σ_b (MPa)	

部分分散比 Partial dispersion rates			
$P_{c,t}$	0.8001	$P'_{c,t}$	0.8391
$P_{d,c}$	0.3007	$P'_{d,c}$	0.2505
$P_{e,d}$	0.2379	$P'_{e,d}$	0.2354
$P_{F,e}$	0.4614	$P'_{F,e}$	0.5141
$P_{g,F}$	0.5589	$P'_{g,F}$	0.4957
$P_{h,g}$	0.4745	$P'_{h,g}$	0.4696
$P_{i,h}$	0.8388	$P'_{i,h}$	0.8302

屈折率の温度係数 Thermal coefficient of refractive indices ($\times 10^{-6}/K$)		
(°C)	dn/dT (rel.)	dn/dT (abs.)
-40/-20	0.3	-1.7
-20/ 0	0.4	-1.3
0/+20	0.5	-1.0
+20/+40	0.6	-0.7
+40/+60	0.6	-0.5
+60/+80	0.6	-0.4

異常分散性 Anomalous dispersions	
$\Delta P_{c,t}$	0.0106
$\Delta P_{c,A'}$	0.0001
$\Delta P_{g,d}$	0.0052
$\Delta P_{g,F}$	0.0045
$\Delta P_{i,g}$	0.0336

光弾性定数 Photoelastic Constant	
B ($10^{-12}/Pa$)	

比重 Specific Gravity	
d	2.43

着色度 Coloration Code	
$\lambda 80 (\lambda 70) / \lambda 5$	365/335
着色度 (内部透過率) Coloration of Internal Transmittance	
$\lambda \tau 80 / \lambda \tau 5$	358/336

備考 Remarks					
硝種対照表 Glass Cross Reference Index					
	HOYA	SCHOTT	OHARA	HIKARI	CDGM
Glass Type	E-CF6		S-NSL36	E-KF6	H-KF6
Code	517-522		517-524	517-523	517-522

作成 201104