

# M-BACD12

## 583-595

$n_d = 1.58313$   $\nu_d = 59.46$   $n_F - n_C = 0.009807$   
 $n_e = 1.58547$   $\nu_e = 59.22$   $n_{F'} - n_{C'} = 0.009887$

屈折率 Refractive Index		
	$\lambda$ (nm)	
$n_t$	1013.98	1.57197
$n_s$	852.11	1.57481
$n_{A'}$	768.19	1.57671
$n_r$	706.52	1.57843
$n_c$	656.27	1.58014
$n_{c'}$	643.85	1.58061
$n_{633}$	632.80	1.58106
$n_D$	589.29	1.58304
$n_d$	587.56	1.58313
$n_e$	546.07	1.58547
$n_F$	486.13	1.58995
$n_{F'}$	479.99	1.59050
$n_g$	435.84	1.59525
$n_h$	404.66	1.59963
$n_i$	365.01	1.60713

分散式の定数 Constants of dispersion formula	
$A_0$	2.4687810
$A_1$	$-1.0626390 \times 10^{-2}$
$A_2$	$1.3251840 \times 10^{-2}$
$A_3$	$4.0486120 \times 10^{-4}$
$A_4$	$-2.9747990 \times 10^{-5}$
$A_5$	$1.8258840 \times 10^{-6}$

部分分散 Partial dispersions	
$n_c - n_t$	0.008165
$n_d - n_c$	0.002992
$n_F - n_d$	0.006815
$n_g - n_F$	0.005300
$n_{c'} - n_t$	0.008641
$n_e - n_{c'}$	0.004855
$n_{F'} - n_e$	0.005032
$n_g - n_{F'}$	0.004744

部分分散比 Partial dispersion rates			
$P_{c,t}$	0.8326	$P'_{c,t}$	0.8740
$P_{d,c}$	0.3051	$P'_{d,c}$	0.2545
$P_{e,d}$	0.2385	$P'_{e,d}$	0.2366
$P_{F,e}$	0.4564	$P'_{F,e}$	0.5090
$P_{g,F}$	0.5404	$P'_{g,F}$	0.4798
$P_{h,g}$	0.4475	$P'_{h,g}$	0.4439
$P_{i,h}$	0.7638	$P'_{i,h}$	0.7577

異常分散性 Anomalous dispersions	
$\Delta P_{c,t}$	0.0089
$\Delta P_{c,A'}$	0.0010
$\Delta P_{g,d}$	-0.0009
$\Delta P_{g,F}$	-0.0008
$\Delta P_{i,g}$	-0.0037

化学的性質 Chemical Properties	
$D_W$	1
$D_A$	3
$T_{Blue}$	3
$D_{NaOH}$	2
$D_{STPP}$	2
$D_0$	2
$D_H$	1

熱的性質 Thermal Properties	
$T_g$ (°C)	500
$T_s$ (°C)	548
$T_{10^{14.5}}$ (°C)	474
$T_{10^{13}}$ (°C)	495
$T_{10^{7.6}}$ (°C)	596
$\alpha_{-30/+70}$ ( $10^{-7}/K$ )	70
$\alpha_{100/300}$ ( $10^{-7}/K$ )	90
$\lambda$ [W/(m·K)]	1.117
$C_p$ [kJ/(kg·K)]	0.816

機械的性質 Mechanical Properties	
$H_K$	575 (6)
$F_A$	110
$E$ (GPa)	90
$G$ (GPa)	35.8
$\mu$	0.252
$\sigma_b$ (MPa)	112

屈折率の温度係数 Thermal coefficient of refractive indices ( $\times 10^{-6}/K$ )		
(°C)	$dn/dT$ (rel.)	$dn/dT$ (abs.)
-40/-20	3.5	1.4
-20/ 0	3.6	1.8
0/+20	3.7	2.1
+20/+40	3.8	2.4
+40/+60	3.8	2.6
+60/+80	3.8	2.7

光弾性定数 Photoelastic Constant	
$B$ ( $10^{-12}/Pa$ )	2.24

比重 Specific Gravity	
$d$	3.01

備考 Remarks					
硝種対照表 Glass Cross Reference Index					
	HOYA	SCHOTT	OHARA	HIKARI	CDGM
Glass Type	M-BACD12	(P-SK57)	L-BAL42	(Q-SK12S)	D-ZK2
Code	583-595	587-596	583-594	586-596	583-594
作成 201104					

内部透過率 Internal Transmittance		
$\lambda$ (nm)	$\tau$ 5mm	$\tau$ 10mm
1550	0.998	0.996
1500	0.998	0.996
1400	0.998	0.996
1300	0.999	0.997
1200	0.998	0.997
1100	0.998	0.996
1060	0.998	0.996
1050	0.998	0.996
1000	0.998	0.995
950	0.998	0.995
900	0.998	0.995
850	0.998	0.996
830	0.998	0.996
800	0.998	0.997
780	0.998	0.996
750	0.999	0.998
700	0.999	0.999
650	0.999	0.999
600	0.999	0.999
550	0.999	0.999
500	0.999	0.999
480	0.999	0.999
460	0.999	0.998
440	0.998	0.996
420	0.998	0.997
400	0.998	0.996
390	0.996	0.993
380	0.994	0.988
370	0.990	0.981
360	0.982	0.964
350	0.964	0.929
340	0.932	0.869
330	0.876	0.768
320	0.782	0.612
310	0.643	0.413
300	0.469	0.220
290	0.297	0.088
280	0.160	0.026

着色度 Coloration Code	
$\lambda 80 (\lambda 70) / \lambda 5$	345/290
着色度 (内部透過率) Coloration of Internal Transmittance	
$\lambda \tau 80 / \lambda \tau 5$	333/285