

M-LAC130

694-532

$n_d = 1.69350$ $\nu_d = 53.20$ $n_F - n_C = 0.013035$
 $n_e = 1.69661$ $\nu_e = 52.97$ $n_{F'} - n_{C'} = 0.013152$

屈折率 Refractive Index		
	λ (nm)	
n_t	1013.98	1.67894
n_s	852.11	1.68257
$n_{A'}$	768.19	1.68504
n_r	706.52	1.68730
n_c	656.27	1.68955
$n_{c'}$	643.85	1.69017
n_{633}	632.80	1.69076
n_D	589.29	1.69338
n_d	587.56	1.69350
n_e	546.07	1.69661
n_F	486.13	1.70258
$n_{F'}$	479.99	1.70333
n_g	435.84	1.70970
n_h	404.66	1.71564
n_i	365.01	1.72581

化学的性質 Chemical Properties	
D_W	1
D_A	4
T_{Blue}	4
D_{NaOH}	2
D_{STPP}	3
D_0	3
D_H	1

内部透過率 Internal Transmittance		
λ (nm)	τ 5mm	τ 10mm
1550	0.999	0.997
1500	0.998	0.997
1400	0.998	0.997
1300	0.999	0.999
1200	0.999	0.999
1100	0.999	0.999
1060	0.999	0.999
1050	0.999	0.999
1000	0.999	0.999
950	0.999	0.999
900	0.999	0.999
850	0.999	0.999
830	0.999	0.999
800	0.999	0.999
780	0.999	0.999
750	0.999	0.999
700	0.999	0.999
650	0.999	0.999
600	0.999	0.999
550	0.999	0.999
500	0.999	0.999
480	0.999	0.999
460	0.998	0.997
440	0.997	0.995
420	0.996	0.992
400	0.993	0.985
390	0.989	0.978
380	0.981	0.963
370	0.967	0.934
360	0.938	0.880
350	0.889	0.791
340	0.815	0.664
330	0.712	0.507
320	0.584	0.341
310	0.443	0.196
300	0.311	0.096
290	0.186	0.035
280		

分散式の定数 Constants of dispersion formula	
A_0	2.8134120
A_1	$-1.3324480 \times 10^{-2}$
A_2	1.9278650×10^{-2}
A_3	4.1244520×10^{-4}
A_4	$-9.9404320 \times 10^{-6}$
A_5	9.6220240×10^{-7}

熱的性質 Thermal Properties	
T_g (°C)	525
T_s (°C)	569
$T_{10^{14.5}}$ (°C)	501
$T_{10^{13}}$ (°C)	520
$T_{10^{7.6}}$ (°C)	610
$\alpha_{-30/+70}$ ($10^{-7}/K$)	69
$\alpha_{100/300}$ ($10^{-7}/K$)	86
λ [W/(m·K)]	1.021
C_p [kJ/(kg·K)]	0.687

部分分散 Partial dispersions	
$n_c - n_t$	0.010604
$n_d - n_c$	0.003955
$n_F - n_d$	0.009080
$n_g - n_F$	0.007124
$n_{c'} - n_t$	0.011232
$n_e - n_{c'}$	0.006434
$n_{F'} - n_e$	0.006718
$n_g - n_{F'}$	0.006379

機械的性質 Mechanical Properties	
H_K	650 (7)
F_A	80
E (GPa)	114
G (GPa)	44.0
μ	0.289
σ_b (MPa)	114

部分分散比 Partial dispersion rates			
$P_{c,t}$	0.8135	$P'_{c,t}$	0.8540
$P_{d,c}$	0.3034	$P'_{d,c}$	0.2530
$P_{e,d}$	0.2384	$P'_{e,d}$	0.2362
$P_{F,e}$	0.4582	$P'_{F,e}$	0.5108
$P_{g,F}$	0.5465	$P'_{g,F}$	0.4850
$P_{h,g}$	0.4553	$P'_{h,g}$	0.4513
$P_{i,h}$	0.7803	$P'_{i,h}$	0.7733

屈折率の温度係数 Thermal coefficient of refractive indices ($\times 10^{-6}/K$)		
(°C)	dn/dT (rel.)	dn/dT (abs.)
-40/-20	4.3	2.0
-20/ 0	4.4	2.5
0/+20	4.6	2.9
+20/+40	4.7	3.2
+40/+60	4.7	3.4
+60/+80	4.8	3.6

光弾性定数 Photoelastic Constant	
B ($10^{-12}/Pa$)	2.01

異常分散性 Anomalous dispersions	
$\Delta P_{c,t}$	0.0190
$\Delta P_{c,A'}$	0.0042
$\Delta P_{g,d}$	-0.0074
$\Delta P_{g,F}$	-0.0059
$\Delta P_{i,g}$	-0.0348

比重 Specific Gravity	
d	3.52

着色度 Coloration Code	
$\lambda 80 (\lambda 70) / \lambda 5$	365/295

着色度 (内部透過率) Coloration of Internal Transmittance	
$\lambda \tau 80 / \lambda \tau 5$	351/293

備考 Remarks					
硝種対照表 Glass Cross Reference Index					
	HOYA	SCHOTT	OHARA	HIKARI	CDGM
Glass Type	M-LAC130		L-LAL13	(Q-LAK13S)	D-LAK6
Code	694-532		694-532	697-533	694-531
作成 201104					